SABIC® PP 5705PR

Polypropylene Homopolymer

SABIC

PROSPECTOR®
www.ulprospector.com

Technical Data

Product Description

SABIC® PP 5705PR is a homopolymer polypropylene resin and is typically used for injection molding applications. Molded parts made from this resin typically exhibits high stiffness, good heat resistance and good flow characteristic.

General

Material Status	• Commercial: Active		
Search for UL Yellow Card	• SABIC • SABIC® PP		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength			ASTM D638
Yield	34.0	MPa	
Break	28.0	MPa	
Flexural Modulus - 1% Secant	1700	MPa	ASTM D790A
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact Strength (23°C)	2.0	kJ/m²	ISO 180
Hardness	**Nominal Value**	**Unit**	**Test Method**
Rockwell Hardness (R-Scale)	105		ASTM D785
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	116	°C	
Vicat Softening Temperature	158	°C	ASTM D1525

Notes

[1] Typical properties: these are not to be construed as specifications.

UL and the UL logo are trademarks of UL LLC © 2022. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Form No. TDS-351747-en
Document Created: Thursday, January 6, 2022
Added to Prospector: September 2021
Last Updated: 12/2/2021

Where to Buy

Supplier

SABIC
Web: http://www.sabic.com/

Distributor

3Polymer (Guangzhou) Chemical Technology Co., Ltd.
Telephone: +86-20-3466-7988
Web: http://3polymer.com
Availability: China

AECTRA
Telephone: +33-4-72-54-36-42
Web: https://www.aectra.fr/
Availability: France

AGI-Augusto Guimarães & Irmão
Telephone: +351-22753-7400
Web: https://www.agi.pt/en/
Availability: Portugal

Distrupol Ltd
Distrupol Ltd is a Pan European distribution company. Contact Distrupol Ltd for availability of individual products by country.
Telephone: 08452003040
Web: http://www.distrupol.com/
Availability: Denmark, Finland, Norway, Sweden

Guzmán Polymers
Telephone: +34-963-992-400
Web: https://www.guzmanglobal.com/en/productos/plastics/
Availability: Italy, Spain, Turkey

Nexeo Plastics
Nexeo Plastics is leading global resin distributor with the technical resources you need to overcome material challenges. Visit us on the web at www.nexeoplastics.com.
Telephone: 833-446-3936
Web: https://www.nexeoplastics.com/
Availability: North America

Plastoplan
Telephone: +43-1-25040-0
Web: https://www.plastoplan.com/
Availability: Czech Republic, Poland, Slovakia

POLYMIX
POLYMIX is a Pan European distribution company. Contact POLYMIX for availability of individual products by country.
Telephone: +33-3-8920-1380
Web: http://www.polymix.eu/
Availability: France

RESINEX Group
RESINEX is a Pan European distribution company. Contact RESINEX for availability of individual products by country.
Telephone: +32-14-672511
Web: http://www.resinex.com/
Availability: Europe

Form No. TDS-351747-en

UL and the UL logo are trademarks of UL LLC © 2022. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Document Created: Thursday, January 6, 2022
Added to Prospector: September 2021
Last Updated: 12/2/2021