J-330
Polypropylene (Impact Copolymer)

Product Description
J-330 is a Impact copolymer polypropylene and is designed suitable for injection molding.
J-330 offers good strength and impact/heat resistance. It is typically used in production of Industrial/Household goods, home appliances and electronics.

Key Features
- Impact/Heat resistance
- Good stiffness

Applications
- Industrial/Household goods
- Home appliances and electronics

Typical Properties

	Item	Measuring Method		Value	Unit
Physical	Melt Flow Index (230℃, 2.16㎏)	ASTM	D1238	4.0	g/10min
	Density	ASTM	D1505	0.9	g/cm^3
Mechanical	Tensile Stress (Yield)	ASTM	D638	280	kgf/cm^2
	Tensile Strain (Break)	ASTM	D638	> 100	%
	Flexural Modulus	ASTM	D790	12,000	kgf/cm^2
	Notched Izod Impact Strength (23℃)	ASTM	D256	10.0	kgf·cm/cm
	Notched Izod Impact Strength (-10℃)	ASTM	D256	3.5	kgf·cm/cm
	Heat Deflection Temp. (4.6kgf/cm^2)	ASTM	D648	105	℃

• NOTE : These are not to be construed as specifications

*Disclaimer : All information in this document is for reference only and is not a final product specification. The content of this document is not legally binding and suitability issues regarding final use must be determined by the user, and the user alone is responsible for the outcome. The values and information specified in this document may change without prior notice for quality enhancement of the product.

www.lottechem.com