ExxonMobil Signature Polymers

ExxonMobil™ LD 07523 Series

Low Density Polyethylene

Product Description

LD 07523 series are LDPE grades, offering good blend mechanical properties and stiffness. Several additive packages are available according to the required surface properties.

General

Availability [1]	▪ Africa & Middle East	▪ Asia Pacific	▪ Europe
Additive	▪ LD 07523.AC: Antiblock: 450 ppm; Slip: 500 ppm; Thermal Stabilizer: Yes ▪ LD 07523.BW: Antiblock: No; Slip: No; Thermal Stabilizer: Yes		
Applications	▪ Agricultural Film ▪ Blend Partner ▪ Co-Extrusion Films	▪ Collation Shrink ▪ Form Fill And Seal Packaging ▪ Freezer Film	▪ Lamination Film ▪ Medium Duty Shrink Film ▪ Shoppers
Form(s)	▪ Pellets		
Revision Date	▪ 01/01/2017		

Resin Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Density	0.923	g/cm³	0.923	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.75	g/10 min	0.75	g/10 min	ASTM D1238
Peak Melting Temperature	229	°F	110	°C	ExxonMobil Method

Film Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Tensile Strength at Break MD	4000	psi	28	MPa	ASTM D882
Tensile Strength at Break TD	3200	psi	22	MPa	ASTM D882
Elongation at Break MD	310	%	310	%	ASTM D882
Elongation at Break TD	530	%	530	%	ASTM D882
Secant Modulus MD - 1% Secant	35000	psi	240	MPa	ASTM D882
Secant Modulus TD - 1% Secant	40000	psi	280	MPa	ASTM D882
Dart Drop Impact	180	g	180	g	ASTM D1709A
Elmendorf Tear Strength MD	350	g	350	g	ASTM D1922
Elmendorf Tear Strength TD	150	g	150	g	ASTM D1922

Optical Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Gloss (45°)	59		59		ASTM D2457
Haze	8.4	%	8.4	%	ASTM D1003

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

The test specimen were prepared on LD 07523.BW, 50µm (1.97mil) thick film, using a 200 mm (7.9 in) die, die gap of 1.0 mm (39.4 mil), Blow-Up Ratio of 2.5 and temperature profile of 180 - 190°C (356 - 374°F).

Notes

Typical properties: these are not to be construed as specifications.

[1] Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

THIEN AN PLASTICS | thienanplastics.com | Hotline / Zalo / WeChat / WhatsApp: +84 389 980 742

ExxonMobil™ LD 07523 Series
Low Density Polyethylene

For additional technical, sales and order assistance: Contact Us

©2026 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com

THIEN AN PLASTICS | thienanplastics.com | Hotline / Zalo / WeChat / WhatsApp: +84 389 980 742