SABIC® PC Resin PC0703R - Asia

Polycarbonate

SABIC

PROSPECTOR®
www.ulprospector.com

Technical Data

Product Description

PC0703R resin is a low flow (MFR = 7 at 300?C/1.2kg), heat and UV stabilized, polycarbonate product with mold release designed for use in the extrusion market. It is available exclusively at www.sabicpc.com

General

Material Status	• Commercial: Active		
UL Yellow Card [1]	• E207780-101295396		
Search for UL Yellow Card	• SABIC • SABIC® PC Resin		
Availability	• Asia Pacific		
Uses	• Construction Applications		
Also Available In	• Europe	• Latin America	• North America

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20	g/cm³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	6.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow			Internal Method
-- [3]	0.50 to 0.70	%	
3.20 mm	0.50 to 0.70	%	
Water Absorption (Saturation, 23°C)	0.35	%	ASTM D570 ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- [4]	2350	MPa	ASTM D638
--	2350	MPa	ISO 527-1/1
Tensile Strength			
Yield [5]	63.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield [5]	6.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Break [5]	> 70	%	ASTM D638
Break	> 70	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span [6]	2300	MPa	ASTM D790
-- [7]	2300	MPa	ISO 178
Flexural Stress			
-- [7, 8]	90.0	MPa	ISO 178
Yield, 50.0 mm Span [6]	90.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	900	J/m	ASTM D256
-30°C [9]	12	kJ/m²	ISO 180/1A
23°C [9]	70	kJ/m²	ISO 180/1A
Unnotched Izod Impact			
23°C	No Break		ASTM D4812 ISO 180/1U
-30°C [9]	No Break		ISO 180/1U
Instrumented Dart Impact			ASTM D3763
23°C, Energy at Peak	65.0	J	

UL and the UL logo are trademarks of UL LLC © 2021. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Document Created: Wednesday, December 22, 2021
Added to Prospector: June 2009
Last Updated: 12/2/2021

Hardness	Nominal Value Unit	Test Method
Rockwell Hardness (R-Scale)	120	ASTM D785 ISO 2039-2
Thermal	**Nominal Value Unit**	**Test Method**
Deflection Temperature Under Load		
0.45 MPa, Unannealed, 3.20 mm	138 °C	ASTM D648
0.45 MPa, Unannealed, 4.00 mm, 64.0 mm Span [10]	138 °C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	127 °C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm, 64.0 mm Span [10]	127 °C	ISO 75-2/Af
Vicat Softening Temperature	144 °C	ISO 306/B50 ASTM D1525 [11]
Ball Pressure Test (123 to 127°C)	Pass	IEC 60695-10-2
CLTE - Flow		
-40 to 95°C	7.0E-5 cm/cm/°C	ASTM E831
23 to 80°C	7.0E-5 cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.20 W/m/K	ASTM C177 ISO 8302
Electrical	**Nominal Value Unit**	**Test Method**
Volume Resistivity	> 1.0E+15 ohms·cm	ASTM D257 IEC 60093
Dielectric Strength (1.60 mm)	27 kV/mm	ASTM D149 IEC 60243-1
Dielectric Constant		ASTM D150 IEC 60250
60 Hz	3.00	
1 MHz	3.00	
Dissipation Factor		ASTM D150 IEC 60250
60 Hz	1.0E-3	
1 MHz	0.010	
Flammability	**Nominal Value Unit**	**Test Method**
Flame Rating (1.6 mm)	V-2	UL 94
Optical	**Nominal Value Unit**	**Test Method**
Refractive Index	1.586	ASTM D542 ISO 489
Light Transmittance (2540 µm)	88.0 to 90.0 %	ASTM D1003
Haze (2540 µm)	< 0.800 %	ASTM D1003

Injection	Nominal Value Unit
Drying Temperature	120 °C
Drying Time	2.0 to 4.0 hr
Suggested Max Moisture	0.020 %
Hopper Temperature	60 to 80 °C
Rear Temperature	270 to 300 °C
Middle Temperature	280 to 310 °C
Front Temperature	290 to 320 °C
Nozzle Temperature	280 to 310 °C
Processing (Melt) Temp	290 to 320 °C
Mold Temperature	80 to 120 °C

Form No. TDS-128720-en

UL and the UL logo are trademarks of UL LLC © 2021. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Document Created: Wednesday, December 22, 2021
Added to Prospector: June 2009
Last Updated: 12/2/2021

Extrusion Notes

Profile Extrusion Parameters

- Drying Temperature: 120°C
- Drying Time: 2 to 4 hr
- Maximum Moisture Content: 0.02%
- Barrel - Zone 1 Temperature: 260 to 280°C
- Barrel - Zone 2 Temperature: 260 to 280°C
- Barrel - Zone 3 Temperature: 260 to 280°C
- Barrel - Zone 4 Temperature: 260 to 280°C
- Hopper Temperature: 40 to 60°C
- Adapter Temperature: 260 to 280°C
- Die Temperature: 250 to 260°C
- Melt Temperature: 270 to 280°C
- Calibrator Temperature: 70 to 90°C

Notes

[1] A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

[2] Typical properties: these are not to be construed as specifications.

[3] Tensile Bar

[4] 50 mm/min

[5] Type I, 50 mm/min

[6] 1.3 mm/min

[7] 2.0 mm/min

[8] at Yield

[9] 80*10*3 mm

[10] 80*10*4 mm

[11] Rate A (50°C/h), Loading 2 (50 N)

UL and the UL logo are trademarks of UL LLC © 2021. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Document Created: Wednesday, December 22, 2021
Added to Prospector: June 2009
Last Updated: 12/2/2021

Where to Buy

Supplier

SABIC
Web: http://www.sabic.com/

Distributor

3Polymer (Guangzhou) Chemical Technology Co., Ltd.
Telephone: +86-20-3466-7988
Web: http://3polymer.com
Availability: China

UL and the UL logo are trademarks of UL LLC © 2021. All Rights Reserved.
UL Prospector | 800-788-4668 or 307-742-9227 | www.ulprospector.com.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Document Created: Wednesday, December 22, 2021
Added to Prospector: June 2009
Last Updated: 12/2/2021