中景石化
ZHONGJING PETROCHEMICAL

POLYPROPYLENE T30S
TYPICAL PROPERTIES

GRADE

Yarn grade

APPLICATIONS

1 Woven bag
2 Scotch tape
3 FIBC

CHARACTERISTICS

With good mechanical resistance, high temperature resistance, good chemical resistance and processability.

PROPERTIES

ITEM			UNIT		VALUE	METHOD
1	Appearance	Black	piece/kg	≤	0	SH/T 1541
2	Fish eye	0.8mm	piece/1520cm²	<	10	GB/T 6595
		0.4mm	piece/1520cm²	<	40	
3	MFR		g/10min		3.0±0.5	GB/T 3682
4	Isotactic Index		%		96.0±2	GB/T 2412
5	Ash Content		mg/kg	<	300	GB/T 9345.1
6	Tensile Strength at Yield		Mpa	>	31.0	GB/T 1040.2
7	Tensile Breaking Strengths		Mpa	>	8.0	
8	Tensile Strained to		%	>	180	

The figures listed in this guide are for reference purposes only; they are not to be used as specification limits.

Please note that this information provided herein might be updated without a previous notice.

Zhongjing Petrochemical makes no warranty of any kind, expressed or implied, regarding to the accuracy of these data

For further requirements, please contact us.