Asrene®

Linear Low Density Polyethylene

Chandra Asri

UI 2650

Density	**0.927**
Melt Index	**50**

CHARACTERISTIC:

- Not UV stabilized
- High flow properties
- Excellent moldability
- Excellent toughness and ESCR

APPLICATION:

- Injection molding
- Lids
- Bottle closures
- Masterbatch
- Powder coating
- Toys

Physical Properties	Test Method*	Unit	Value
Density	ASTM D 1505	g/cm^3	0.927
MI (190 °C/2.16 kg)	ASTM D 1238	g/10 min.	50
Vicat softening temperature	ASTM D 1525	°C	90
Brittleness temperature	ASTM D 746	°C	< -70
ESCR [F_{50}]	ASTM D 1693	Hrs	30
Tensile strength @ yield	ASTM D 638	MPa	18
Elongation @ break	ASTM D 638	%	100
Flexural modulus	ASTM D 790	MPa	600
Izod impact strength	ASTM D 256	kJ/m^2	40

*Polyethylene tested per ASTM D 1928

Conversions: 1 MPa = 10.2 kgf/cm^2
1 kJ/m^2 = 0.01 $kgf.cm/mm^2$

Recommended Processing Conditions:

Melt Temperature ……..175 - 225 °C

This material complies with recommendations & statutory regulations in the USA, Japan and most European countries regarding packaging materials intended to come in contact with foodstuff.

The nominal properties reported herein are typical of the product of CAPC but do not reflect normal testing variance and therefore should not to be construed as specifications.

CAPC reserves the right to make any improvement or amendments to the composition of any grade or product without alteration to the product code.

This document reports accurate and reliable information to the best of our knowledge on the products manufactured by CAPC. Since CAPC can not anticipate or control the conditions under which this information and its product may be used, each user should review the information in the specific context of the intended application. CAPC will not be responsible for damages of any nature resulting from the use of or reliance upon the information.

This technical datasheet is effective as from January 2008 and supersedes all previously published data.

PT Chandra Asri
Jl. Raya Anyer Km. 123
Ciwandan, Cilegon
Banten 42447, Indonesia
T 62(254) 601 501 F 62(254) 601 505
www.chandra-asri.com

ISO 14001:2004 SGS CERTIFICATE NO. GB02/54337
ISO 9001:2000 SGS CERTIFICATE NO. ID07/0963