HDPE

HDPE for Pressure Pipe

▶XS10N

● Description

HDPE XS10N is a high density polyethylene, with a MRS 10MPa – PE100 classification, containing hexene as co-monomer and is produced by a bimodal slurry loop process.

● Characteristics

- ▶ meeting the highest prescription and standards for PE pipe
- ▶ easy processing and safe welding properties
- ▶ UV stabilization

● Applications

- ▶ Portable water, Sewage, Industrial pipe

● Physical Properties

Properties	Test Method	Units	XS10N
Melt Index (190℃/5kg)	ISO 1133	g/10min	0.3
Density	ISO 1183	g/cm^3	0.948
Oxygen Induction Time (200℃)	ISO 11357-6	min	>20
Water Content	ISO 15512	ppm	≤300
Melting Temperature	Hanwha Total		129
Tensile Strength at Yield	ISO 527	MPa	26
Tensile Strength at Break	ISO 527	MPa	35
Elongation at Break	ISO 527	%	≥700
Flexural Modulus	ISO 178	MPa	1,100

*These are typical property values and are not to be construed as specifications.

● Contacts

▶ **Polymer Application Tech. Team**

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do,
Korea, 31900

TEL : 82-41-660-6190 FAX : 82-41-660-6189

Disclaimer

This document is copyright of Hanwha Total petrochemical Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.